

Certificate Ref: 3000403863R

Order Ref: PO-03179
Received: 09/11/2018
Re-issue Date: 07/01/2019

Bend Test

Laboratory Temperature	21 °C
Bend Radius	2 x thickness
Face Bend	Bent 180° without cracking.
Result	Acceptable

Metallographic Examination

Magnification	x50 - x500
Etchant	B.O.S.
Section(s) assessed	1
Result	Acceptable

Note

*The sample is acceptable to C.A.A. A8-10, however it is not acceptable to BS ISO 24394:2008 + A1:2012 due to excessive linear misalignment.

Reason for re-issue: Additional Test Schedules and Notes added.

Test Schedule: C.A.A. - British Civil Airworthiness Requirements Chapter A8-10 as applicable.
Test Schedule: Rolls Royce Plc RPS 912 Iss 18 as applicable.
Test Schedule: British Standard BS ISO 24394:2008 + A1:2012 as applicable.

*** END OF DOCUMENT ***



0034

